

Permafab

Polyester reinforcing fabric

FEATURES

Highly Conformable
Polyester Technology
Open Weave

BENEFITS

- Conforms to even the most difficult details
- Non rotting, moisture resistant material
- Allows for improved wetting characteristics

DESCRIPTION

Permafab is 100% stitchbonded, polyester reinforcing fabric.

BASIC USES

Permafab is designed to be used in conjunction with designated Tremco liquid-applied products providing additional stability and strength properties to the application.

PACKAGING

4" x 300' roll (101.6 mm x 7.62 m)
6" x 300' roll (152.4 mm x 7.62 m)
12" x 300' roll (304.8 mm x 7.62m)
40" x 324' roll (1016 mm x 8.23 m)

COLOR

White

STORAGE

DO NOT ALLOW ROLLS TO BECOME WET

Recommended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition sources and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Performance could be affected if the product is not stored properly.

APPLICATION

Follow preparation/application recommendations for liquid applied products being used in conjunction with Permafab.

Apply Permafab as it comes off the roll. Do not flip or invert the reinforcement during use.

Fully-Reinforced Application: Fully embed Permafab into wet liquid applied product using a brush or roller until reinforcement is fully saturated and is free of voids, wrinkles, air pockets, standing fibers, etc. In overlap areas ensure wet product is present on the top of the embedded sheet and overlap side laps a minimum of 3" (76 mm) and end laps a minimum of 6" (152 mm). Follow the same guidelines to embed the reinforcement in these areas. Do not allow foot traffic on Permafab during application or until liquid product has cured. Once cured, apply top coat at the specified rate fully covering the embedded Permafab.

Partially-Reinforced System Application: Install a three-course application on all drainage components, field laps/seams, flashing base and vertical laps/seams, penetrations, etc. following Tremco detail guidelines. Install the three-course application fully embedding Permafab into wet liquid applied product using a brush or roller until reinforcement is fully saturated and is free of voids, wrinkles, air pockets, standing fibers, etc. Then fully encapsulate the Permafab with an additional application liquid applied product.

COVERAGE RATES

4" x 300' - Approx. 100 sq. ft. (9.2 m²)
6" x 300' - Approx. 150 sq. ft. (13.9 m²)
12" x 300' - Approx. 300 sq. ft. (27.8 m²)
40" x 324' roll - Approx. 1,080 sq. ft. (100.3 m²)

NOTE: Coverage rates do not account for overlapped areas.

LIMITATIONS

Refer to the liquid-applied product data sheet for specific application information.

PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUE
Ball Burst	ASTM D3787	90 lbs (40.8 kg)
Elongation	ASTM D5034 (1" Jaws)	MD - 25% XMD - 100%
Elongation	ASTM D5034 (2" Jaws)	MD - 25% XMD - 75%
Tear Strength	ASTM D5587	MD - 20 lbs (9.0 kg) XMD - 20 lbs (9.0 kg)
Tensile Strength	ASTM D5034 (1" Jaws)	MD - 55 lbs (24.9 kg) XMD - 60 lbs (27.2 kg)
Tensile Strength	ASTM D5034 (2" Jaws)	MD - 110 lbs (49.8 kg) XMD - 60 lbs (27.2 kg)
Thickness	ASTM D1777	0.018 in

CODES & APPROVALS

Florida Building Code



MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



3735 Green Road
Beachwood, Ohio 44122
220 Wicksteed Avenue
Toronto, Ontario, M4H 1G7
www.tremcoroofing.com
1.800.852.6013

Tremco Roofing and Building Maintenance is part of Tremco Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.
The information provided on this data page supersedes all previous data concerning this product and its application.
The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury to person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.