

TREMprime WB

A Quick-Drying Water Based Asphaltic Primer

Composition: TREMprime WB is a water based polymer modified asphalt primer formulated from refined select asphalt, special adhesion, promoters and synthetic polymers which conditions a variety of roofing substrates prior to the application of Tremco Roofing Systems and coatings. TREMprime WB is asbestos free, easy to use, and is low in volatile organic compounds to meet the requirements of the National Architectural Coatings regulation.

Basic Use: TREMprime WB promotes adhesion between new and weathered surfaces and Tremco Roofing Systems and coatings.

Limitations:

- Not intended to be used as a final coating.
- Do not apply when rain appears imminent.
- Do not apply below 45°F (7°C).
- Do not freeze container.
- Store indoors in a heated area.
- Surfaces primed with Tremprime WB must be reprimed if open for more than 24 hours.

Product Advantages	
Features	Benefits
Non-fibrated	<ul style="list-style-type: none"> • Allows maximum penetration of dried felts and porous substrates
Adhesion promoters	<ul style="list-style-type: none"> • Conditions asphalts and felts to provide highly receptive surface for protection treatments
Quick drying formula	<ul style="list-style-type: none"> • Minimizes wait for curing
Readily workable consistency	<ul style="list-style-type: none"> • Easily brushes into rougher substrates providing more uniform surfaces • Can be used on metal-work and other surfaces
Water based	<ul style="list-style-type: none"> • Environmentally cleaner • Meets VOC standards

Grade: Brush/roll/spray.

Recommended Spray Equipment: Minimum 11:1 ratio pump with 0.015" to 0.021" spray tip.

Packaging: TREMprime WB is available in 1 gallon (3.78L), 5 gallon (19L) containers and 53 gallon (200L) plastic lined drums.

Storage Life: One year.

Application: Remove all loose dust, dirt, rotted felt, and foreign matter. Surface must be clean and dry. When spraying Tremprime WB take necessary precautions to prevent overspray.

Coverage: Coverage will vary depending upon actual surface and application conditions. Approximately 200-400 sq ft/gal (4.9-9.8 m²/L).

Clean-up: Promptly clean tools and equipment with soap and water. Dried primer can be cleaned with mineral spirits.

Precautions: Use TREMprime WB with adequate ventilation. Users must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

Availability and Cost: Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

Maintenance: Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Guarantee/Warranty: Tremco Inc. warrants TREMprime WB to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any TREMprime WB product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYERS SOLE AND EXCLUSIVE REMEDY.

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

Technical Services: Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

Statement of Policy and Responsibility: Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.

Physical Performance Characteristics		
TREMprime WB		
Property	Typical Value	Test Method
Asbestos content	None	EPA 600/R-93/116
Viscosity @ 77°F (25°C) (Stormer Krieb)	50 KU	ASTM D 562
Density @ 77°F (25°C)	8.5 lb/gal (1018 kg/m ³)	ASTM D 1475
Nonvolatile content	46%	ASTM D 2823
Flash Point	Not applicable	ASTM D 3278
pH	9.1	ASTM E 70
VOC	2 g/l	ASTM D 3960
Color	Brown/black	

TREMCO 3735 Green Road
Beachwood, OH 44122
216-292-5000

220 Wicksteed Ave
Toronto, ONT M4H 1G7
416-421-3300