Premium III Pak-Free Asphalt

A Quality Controlled, Low Odor Hot-Melt Adhesive Packaged in Meltable Plastic Film

FEATURES

BENEFITS

Consumable packaging

Quality controlled product

Less packaging waste

Consistent performance values

UL & FM Approved

Fire/wind protection

DESCRIPTION

Premium III Pak-Free Asphalt is a high quality roof mopping asphalt processed from a closely monitored asphalt flux, and packaged in easy to handle polyethylene plastic wrappers. The wrapping plastic on each package is suitable for placement in a standard roofing hot-kettle without removing it from the asphalt. In addition, a compatible low odor additive is blended within the hot melt to reduce jobsite odors. Premium III Pak-Free Asphalt meets tightly controlled performance characteristics and performs in accordance with ASTM D 312, the Standard Specification for Asphalt Used in Roofing.

BASIC USES

Premium III Pak-Free Asphalt is designed for application as a thermoplastic hot melt adhesive in a variety of built-up roof configurations. The Pak-Free packaging helps reduce jobsite waste by eliminating asphalt keg containers and increasing the amount of asphalt which may be shipped per pallet. The meltable polyethylene wrapper is not removed from each asphalt package, instead, is placed in the hot kettle as a unit and melts away.

Premium III Pak-Free Asphalt is suitable for use as an interply adhesive for standard built up roofs, especially for steep-sloped roof applications. In addition, Premium III Pak-Free Asphalt may be used as a flood coat surfacing adhesive for asphalt built up and SBS modified bitumen roof systems, along with being recommended for use to adhere Tremco approved roof insulation boards to acceptable substrates.

PACKAGING

Available in 50 lb (22.5 kg) units, individually wrapped in a meltable polyethylene film. Sold by the pallet only.

Two pallet sizes are offered. Pallet size is based on regional availability.

- 2,500 lbs (1,134 kg) per pallet 50 units
- 2,000 lbs (907 kg) per pallet 40 units

APPLICATION

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, and rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based upon your roof's conditions.

Structural Deck: Must be properly designed and structurally sound.

Drainage: Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or an approved cellular concrete slope system.

APPLICATION

Premium III Pak-Free Asphalt

Insulation: Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day. The use of FAS-n-FREE Adhesive for solvent

free fastener free insulation attachment is the preferred method of securement, unless otherwise specified.

Acceptable Insulations:

MINIMUM THICKNESS*	FACER
1/2" (13mm)	Coated
1" (25mm)	None
1/2" (13mm)	None
1" (25mm)	None
1" (25mm)	Black/white
	1″ (25mm) 1/2″ (13mm) 1″ (25mm)

Maximum size: 4' x 8' (1219mm x 2438mm)

* Minimum thickness for application of Premium III. Follow insulation manufacturer's instructions to obtain minimum thickness for spanning metal deck ribs.

Installation Procedures: According to particular project specifications, prepare surface to be covered:

- Replace areas of wet insulation, deteriorated deck, and wood components.
- Install roof insulation or base sheet by mechanical attachment or in a uniform and continuous mopping of Premium III applied at 25-30lb/100 ft² (1.2 - 1.4 kg/m²).

Plan placement of roofing ply sheets to ensure that water will flow over or along, but not against exposed edges. Use standard kettle equipped with circulating pump. Do not heat Premium III above its flash point. Starting at low point of roof, apply a uniform continuous mopping of Premium III using standard roofing mop or Tremco approved felt layer.

Use ply sheets to start and finish roof membrane along edges, terminations and projections as specified. Install ply sheets, overlapping each previous ply the specified width. Embed each ply in uniform and continuous mopping of Premium III asphalt, applied within its Equiviscous Temperature (EVT) range.

Interply application rate:	FELT	LB/100 FT ^{2*}
	BURmastic Glass Ply	25 (1.2 kg/m²)
	Burmastic Composite Ply	25 (1.2 kg/m²)
	Poly-THERM	25 (1.2 kg/m²)
	THERMglass	25 (1.2 kg/m²)
	POWERply MB systems (all plies)	25 (1.2 kg/m²)
* Application Tolerance: +	-20%	

Application Iolerance: +20%

Ply shall never touch ply. Apply Premium III Pak-Free Asphalt no more than ten feet ahead of each roll. Lightly broom plies from unmopped side to assure complete adhesion. Tie in previous work 24" (600mm). Lap ply sheet ends 6" (150mm). Stagger end laps. Avoid walking on plies until Premium III Pak-Free Asphalt has cooled. Install flashings as specified.

Gravel: Apply Premium III Pak-Free Asphalt over roof surface at 60 lb/100 ft² (2.9 kg/m²) + 20%. Immediately broadcast 400 lb/100 ft² (19.5 kg/m²) of new, clean gravel or 300 lb/100 ft² (14.5 kg/m²) of slag into adhesive. Aggregate shall conform to ASTM D 1863.

Smooth Surface: Consult your local Tremco Representative for specific applications suitable for your geographic area.

Premium III Pak-Free Asphalt quantities for waterstop/tieoffs, flashings, miscellaneous detail applications and minimum kettle capacity are not included in inter-ply and flood coat application rates.

SURFACING OPTIONS

APPLICATION RATE

LIMITATIONS

PHYSICAL PROPERTIES

• Not intended to perform under ponding conditions. Positive drainage required.

Premium III Pak-Free Asphalt

- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.
- Not for use over expanded polystyrene (EPS) or EPS composite insulations installed in any configuration unless EPS is encapsulated within lightweight insulating cellular concrete.
- Not for hot applying membrane systems directly over isocyanurate insulation. Isocyanurate insulations must be overlayed with either 1/2" (13mm) fiberboard, 3/4" (19mm) fibrous glass, or 1"(25mm) perlite (minimum thicknesses).
- Not for use over phenolic insulations installed in any configuration.
- Backnail felts on roofs with slopes 2:12 (2" per foot) or greater. Do not install on roofs with slopes greater than 3:12 (3" per foot).
- Do not install when ambient temperatures are below 50°F (10°C) unless special cold weather application procedures are followed. Consult your local Tremco Representative for details.

PROPERTY	TYPICAL VALUE	TEST METHOD
Softening Point	195 - 205°F (90.5 - 96°C)	ASTM D 36
Penetration @ 77°F	15 - 30 dmm	ASTM D 5
Flash Point, min	525°F (274°C)	ASTM D92
Ductility @ 77°F	2.5 cm	ASTM D113
EVT (125 cP)	400-450°F (204 - 221°C)	ASTM 4402

PRECAUTIONS

MAINTENANCE

TECHNICAL SUPPORT



Roofing & Building Maintenance www.tremcoroofing.com 3735 Green Road Beachwood, Ohio 44122 1.800.852.6013

50 Beth Nealson Drive Toronto, Ontario M4H 1M6 1.800.668.9879 Tremco Roofing & Building Maintenance is a part of the Tremco Construction Products Group

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the service of the Tremco Service Staff.

Tremco is a US Registered trademark of Tremco Incorporated.

Tremco is a US Registered trademark of Tremco Incorporated. The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO SE INABLE FOR CONSEQUENTIAL OF INCLEDIATION ANY REFACH OF WARRANTY IN ALL CASES TERMCO'S LIABILITY IS I HABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING