

THERMastic 100

Elastomeric modified bitumen hot melt

FEATURES

- Elastomeric properties
- Superior weathering properties
- Cold weather performance

BENEFITS

- Ensures high elongation and superior low temperature flexibility
- In comparison to conventional asphalt
- Excellent adhesive properties e at lower temperatures

DESCRIPTION

THERMastic 100 adhesive is a proprietary polymeric formulation incorporating a high quality unblown asphalt and select (SEBS) polymers. THERMastic 100 is a mopping grade, elastomeric modified bitumen hot melt adhesive for delivering superior waterproofing and weathering properties.

BASIC USES

THERMastic 100 is designed for application as an elastomeric modified bitumen hot melt in a variety of built-up roof configurations. THERMastic 100 can be used as an interply adhesive for prefabricated modified bitumen systems as well as an interply and floodcoat for premium performance built-up roofs.

PACKAGING

THERMastic 100 is available in 27.2 kg (60 lb) kegs, 9 kegs per pallet.

APPLICATION

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based on the condition of your roof.

Drainage: Excessive ponding conditions can adversely affect the performance of any roof system. Where positive drainage does not exist, water removal from the roof surface must be facilitated by lowering sumps, installing tapered insulation or additional drains.

Application:

- Ensure bonding surfaces are uncontaminated, clean, dry and free of any loose foreign matter.
- Heat THERMastic 100 in a clean asphalt kettle equipped with a recirculating pump. Follow instructions on label.
- THERMastic 100 quantities for waterstop/tie-offs, flashings, miscellaneous detail applications and minimum kettle capacity are not included in interply and flood coat application rates.

Mopping Coverages (minimum):

Interply - 1.2 kg/sqm (25 lb/sq)

Floodcoat - 2.7 kg/sqm (55 lb/sq)

The floodcoat can be finished off with either granules or gravel.

- Material temperature during heating must not exceed 275°C (527°F).
- THERMastic 100 should not be exposed to solvents, oils or other contaminants harmful to asphaltic materials.

LIMITATIONS

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Softening Pt (C)	90 - 96	ASTM D3461
Elongation (%)	>900	ASTM D 412
Low Temp Flexibility(°C)	-20 to -25	ASTM D 3111
Weatherability	Very Good	QUV Tester 60C/condens'n/-20C cycling

CODES & APPROVALS


MAINTENANCE

PRECAUTIONS

TECHNICAL SUPPORT

THERMastic 100

Approved for use in a variety of UL and FM classified assemblies.



Your local Tremco Roofing Sales Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing Sales Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.
The information provided on this data page supersedes all previous data concerning this product and its application.
The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.