

# AlphaGuard™ C-Prime

## *Two Component, 100% Solids Epoxy Primer for Concrete and Masonry Surfaces*

### DESCRIPTION

AlphaGuard C-Prime is a 100% solids, two component, low VOC, low odor epoxy penetrating primer.

### BASIC USES

C-Prime is used to prime concrete and masonry surfaces prior to application of AlphaGuard BIO and MT/MTS systems.

### PACKAGING

#### **4 gal (15.1 L) Kits**

Part A (2 per kit) - 1 gal (3.7 L) can  
Part B (2 per kit) - 1 gal (3.7 L) can

#### **10 gal (37.8 L) Kits**

Part A - 5 gal (18.9 L) pail  
Part B - 5 gal (18.9 L) pail

### COLOR

Amber

### GRADE

Brush, Roller, Squeegee & Backroll

### POT LIFE

10-20 minutes at 75°F (24°C) / 50% RH

*\*Temperature dependent - Increasing ambient and product temperatures reduce expected pot life.*

### STORAGE

12 months shelf life in unopened containers when properly stored.

Recommended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition sources and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be affected if the product is not stored properly.

### APPLICATION

**Surface Preparation:** Allow new concrete to cure for a minimum of 28 days and until moisture, RH, and compressive strength values reach an appropriate level. Concrete must be structurally sound, dry, free of grease, oils, coatings, dust, curing compounds and other contaminants. Surface laitance must be removed. Remove defective concrete, honeycombs, cavities, joint cracks, voids and other defects by routing to sound material. Concrete surfaces must be shot-blasted to an ICRI 3-6 surface profile. Prior to application, test pull off strength of proposed system following ASTM D4541 and ensure the moisture content in the concrete surface measures lower than 5% following ASTM F2659.

**Mixing:** Add equal parts of Part A and Part B into a clean, dry mixing container. Using a heavy duty corded power drill with Jiffy Mixer mixing blade, mix the combined materials for 3-5 minutes minimum until product is uniform in appearance and consistency. Make sure to mix areas around side walls and bottom of pail. Improper mixing will result in non-curing material. Do not thin.

# AlphaGuard™ C-Prime

## APPLICATION CONTINUED

## ACCEPTABLE ROOF SURFACES

## COVERAGE RATES

## TEMPERATURE/WEATHER RECOMMENDATIONS

## CURE TIMES

## LIMITATIONS

## TECHNICAL DATA

## MAINTENANCE

## PRECAUTIONS

## TECHNICAL SUPPORT



Roofing & Building Maintenance

www.tremcoroofing.com  
3735 Green Road  
Beachwood, Ohio 44122  
1.800.852.6013

50 Beth Neilson Drive  
Toronto, Ontario M4H 1M6  
1.800.668.9879

Tremco Roofing & Building Maintenance is  
a part of the Tremco Construction Products  
Group

**Installation:** Install product using one of the approved application methods evenly at the recommended coverage rate. Use wet mil gauges to monitor coverage rates throughout application. Never fully invert empty pails in an attempt to drain material as this may result in improperly cured material during application. Allow primer to cure prior to top coating. Primer must be top coated within 3 days of application. After 3 days, re-priming will be necessary.

Smooth BUR	Gravel BUR	Concrete	Foam	Modified Bitumen	Metal	Single Ply	SPUF	Walls
		•						

200 - 250 sq. ft. per gallon (5-6 m<sup>2</sup>/L).

*Note: Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate.*

**Min Ambient:** 50°F (10°C)

**Max Ambient:** 90°F (32°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.7°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product

**Gel Time:** 30-40 minutes @ 75°F (24°C) / 50% RH

**Tack Free Time:** 3-4 hours @ 75°F (24°C) / 50% RH

*Note: Cure times can be effected by a number of weather and jobsite conditions including but not limited to exposure to sunlight and wind, humidity, precipitation, and temperature.*

Before the product cures, clean surfaces and equipment with water and soap.

Not recommended for use over the following:

**Roof Decks:** Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

**Products/Systems:** Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, corrugated or standing seam metal roof systems, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tar-based products.

- Not for use under continuous immersion.

PROPERTY	TEST METHOD	TYPICAL VALUE
Mix Ratio		1:1 (A+B by volume)
Mixed Viscosity		300-400 cps
Volume Solids		100%
Weight Solids		100%
Mixed VOC		97 g/L

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.

Tremco is a US Registered trademark of Tremco Incorporated.  
The information provided on this data page supersedes all previous data concerning this product and its application.  
The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.