AlphaGuard[™] Glass Mat

DESC

BA

P

Conformable, Rapid Wetting Glass Mat Reinforcement

FI	EATURES	BENEFITS		
	High Conformable	• Conforms to even the most difficult details		
	Fiberglass	• Non rotting, fire resistant material		
	Polyester Binder	• Highly soluble powdered binder allows for open weave and improved wetting characteristics		
RIPTION		Glass Mat is a medium- fine fiber, rapid wetting chopped strand mat. Glass Mat is used as a field and flashings reinforcement for AlphaGuard PLUS and restoration		
	system appl	lications. This durable, long lasting reinforcement provides additional strength, stability, and hroughout the service life of the system.		
ACKAGII		′ (1.2 m x 91.1m) roll ′′ (0.6 m x 91.1m) roll		
CO	LOR White			
STOR	Recom source drop On t area	T ALLOW ROLLS TO BECOME WET mended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition es and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not below 32°F (0°C) or exceed 110°F (43°C). the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated a. Materials should be covered with a light-colored, reflective tarp for protection against the ements. Allow for adequate air flow inside the pallets.		
1 Alexandre	Pe	erformance could be affected if the product is not stored properly.		
APP		Follow preparation/application recommendations for AlphaGuard products being used in conjunction with AlphaGuard Glass Mat.		
		Apply AlphaGuard Glass Mat as it comes off the roll. Do not flip or invert the reinforcement during use.		
		Fully-Reinforced Application: Fully embed AlphaGuard Glass Mat into wet AlphaGuard product using a brush or roller until reinforcement is fully saturated and is free of voids, wrinkles, air pockets, standing fibers, etc. In overlap areas ensure wet product is present on the top of the embedded sheet and overlap side laps a minimum of 3" (76 mm) and end laps a minimum of 6" (152 mm). Follow the same guidelines to embed the reinforcement in these areas. Do not allow foot traffic on AlphaGuard Glass Mat during application or until liquid product has cured. Once cured, apply top coat at the specified rate fully covering the embedded AlphaGuard Glass Mat.		
co	VERAGE RATES	50" x 299' roll - Approx. 1,100 sq. ft. (102 m ²) 25" x 299' roll - Approx. 550 sq. ft. (51 m ²)		

LIMITATIONS

PHYSICAL PROPERTIES

CODES & APPROVALS

MAINTENANCE

PRECAUTIONS

TECHNICAL SUPPORT

Not recommended for use over the following:

AlphaGuard[™] Glass Mat

Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, corrugated or standing seam metal roof systems, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tarbased products.

• Not for use under continuous immersion.

PROPERTY	TEST METHOD	TYPICAL VALUE
Weight Uniformity	W-01FC-T6	225 g/m ²
Loss on Ignition (%)	W-05EC-T6	3.9

Florida Building Code



Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.

TREM(QO)

Roofing & Building Maintenance

ww.tremcoroofing.com 3735 Green Road Beachwood, Ohio 44122 .800.852.6013

50 Beth Nealson Drive Toronto, Ontario M4H 1M6 1.800.668.9879

Tremco Roofing & Building Maintenance is a part of the Tremco Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated. The information provided on this data page supersedes all previous data concerning this product and its application. The Statement provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.