AlphaGuard[™] M-Prime

Primer for metal and plastic surfaces prior to application of urethane-based liquid products and sealants

DESCRIPTION BASIC USES

AlphaGuard M-Prime is a low-VOC, water-based, quick-drying, single component primer.

BASIC USES

PACKAGING

COLOR GRADE STORAGE phaodard with thine is a low-voc, water-based, quick-drying, single component primer.

AlphaGuard M-Prime is designed as an adhesion promoter for urethane liquid products and sealants on nonporous surfaces such as metal and plastics.

1 gal (3.7L) can 1 quart (0.9 L) can

Red

Brush, Clean Rag, Roller

12 months shelf life in unopened containers when properly stored.

DO NOT FREEZE

Recommended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition sources and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be affected if the product is not stored properly.

APPLICATION

Surface Preparation: Surface must be clean, dry, in sound condition, and free of dirt, debris, and contaminants. Deficient areas of existing system must be repaired. All repairs should be made with like materials matching the existing components and allowed to properly cure prior to application of liquid-applied products.

Metal surfaces and coated metal including fluoropolymer/PVDF coatings such as Kynar® (Registered trademark of Arkema Inc.) and Hylar® (Registered trademark of Solvay Solexis Inc.) must be ground to clean bright metal free of rust and primed prior to application.

Installation: Install product using one of the approved application methods evenly at the recommended coverage rate.

Urethane-based liquid products and sealants can be installed up to 8 hours after AlphaGuard M-Prime has been applied and cured. After 8 hours, the surface must be cleaned with MEK or Xylene and re-primed with AlphaGuard M-Prime.

AlphaGuard M-Prime can discolor surfaces to which it is applied. Mask off adjacent areas to prevent staining.

COVERAGE RATES

TEMPERATURE/WEATHER RECOMMENDATIONS

CURE TIMES

CLEAN UP

LIMITATIONS

PHYSICAL PROPERTIES

MAINTENANCE

PRECAUTIONS

TECHNICAL SUPPORT

www.tremcoroofing.com 3735 Green Road Beachwood, Ohio 44122 1.800.852.6013

50 Beth Nealson Drive Toronto, Ontario M4H 1M6 1.800.668.9879

Tremco Roofing & Building Maintenance is a part of the Tremco Construction Products Group

AlphaGuard[™] M-Prime

1,400 - 1,800 sq. ft. / gal (34 - 44 m²/ L)

Note: Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate.

Min Ambient: 50°F (10°C)

Max Ambient: 110°F (43°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.7°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product
- Do not apply when temperatures could fall below 32°F (0°C) within 24 hours of application.

Recoat Time: 15 minutes @ 77°F (25°C) / 50% RH

Note: Cure times can be effected by a number of weather and jobsite conditions including but not limited to exposure to sunlight and wind, humidity, precipitation, and temperature.

Clean equipment with ethyl alcohol. Any spills or over-coating must be cleaned immediately before product dries.

Not recommended for use over the following:

Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, corrugated or standing seam metal roof systems, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tarbased products.

• Not for use under continuous immersion.

PROPERTY	TEST METHOD	TYPICAL VALUE
Density @ 77°F (25°C)	ASTM D1475-90	8.3 lb/gal (1 kg/L)
Asbestos Content	ASTM D276-87	None
VOC	ASTM D3960-89	20 g/L
Nonvolatile content	ASTM D2369-87	5%

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Terroco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.