

AlphaGuard™ PUMA Primer - 107

Two-Component, Methyl Methacrylate Primer

DESCRIPTION

AlphaGuard PUMA Primer - 107 is a two-component, methyl methacrylate primer resin for concrete substrates and metal details.

BASIC USES

AlphaGuard PUMA Primer - 107 is used in conjunction with the AlphaGuard PUMA system to provide adhesion to concrete and metal details.

PACKAGING

Available in 6 gallon (22.71 L) containers

COLOR

Amber

GRADE

Brush / Roller

POT LIFE

10 - 15 minutes. **Pot life dependent on ambient, substrate, and product temperature and the amount of AlphaGuard PUMA Catalyst used.*

STORAGE LIFE

12 months shelf life in unopened containers when properly stored.

DO NOT FREEZE

Recommended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition sources and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be affected if the product is not stored properly.

APPLICATION

Surface Preparation: Surface must be clean, dry, in sound condition, and free of dirt, debris, and contaminants. Rust must be abraded until it no longer exhibits flaking or chalking. Existing wet roofing components must be identified and replaced. Deficient areas of existing system must be repaired. All repairs should be made with like materials matching the existing components and allowed to properly cure prior to application of liquid-applied products.

Allow new concrete to cure for a minimum of 28 days and until moisture, RH, and compressive strength values reach an appropriate level. Concrete surfaces must be shot-blasted to a an ICRI 3-6 surface profile.

Metal surfaces and coated metal including fluoropolymer/PVDF coatings such as Kynar® (Registered trademark of Arkema Inc.) and Hylar® (Registered trademark of Solvay Solexis Inc.) must be ground to clean bright metal free of rust and primed prior to application.

If the surface has a pre-existing coating, paint, or sealant, please contact Tremco for adhesion/compatibility testing and surface preparation recommendations.

AlphaGuard™ PUMA Primer - 107

APPLICATION CONTINUED

Mixing: Use a heavy duty power drill with Jiffy Mixer attachment. Cordless drills are not recommended and may not properly mix the materials. AlphaGuard PUMA Primer - 107 must be mixed to achieve a uniform distribution and appearance of the product. Once properly mixed, AlphaGuard PUMA Primer - 107 can be poured off in smaller quantities into a second container. Add the appropriate amount of AlphaGuard PUMA Catalyst to the selected amount of AlphaGuard Primer - 107 and mix thoroughly until powder catalyst is completely dissolved. Catalyze only the amount of AlphaGuard Primer - 107 intended to be used within the expected pot life. The amount of AlphaGuard PUMA Catalyst required is based on the amount of AlphaGuard Primer - 107 used and the ambient weather conditions (Refer to the mixing chart for proper mixing ratios.).

Install product using one of the approved application methods evenly at the recommended coverage rate. Use wet mil gauges to monitor coverage rates throughout application.

MIXING CHART

AG PUMA PRIMER - 107 AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C) 2% Catalyst			60-70°F (15-21°C) 4% Catalyst			40-60°F (5-15°C) 8% Catalyst			32-40°F (0-5°C) 12% Catalyst			< 32°F (< 0°C)		
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (4.13 lbs) 1.89 L (1.87 kg)	1	0.08	37	3	0.16	75	6	0.33	150	9	0.49	224			
1 gal (8.26 lbs) 3.78 L (3.74 kg)	3	0.16	75	6	0.33	150	12	0.66	299	18	0.99	449			
3 gal (24.78 lbs) 11.34 L (11.24 kg)	9	0.50	225	18	0.99	450	36	1.98	899	54	2.97	1,349			
6 gal (49.56 lbs) 22.68 L (22.48 kg)	16	0.99	450	32	1.98	899	63	3.96	1,798	95	5.95	2,698			

*AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

Smooth BUR	Gravel BUR	Concrete	Foam	Modified Bitumen	Metal	Single Ply	SPUF	Walls
		●			●	●*		

*Field adhesion test and Product/Technical Management approval required

1 gallon / 100 sq. ft. (16 wet mils) (0.4 L/m²)

Min Ambient: -20°F (-28°C)

Max Ambient: 95°F (35°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.7°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product

Dry Time: 20-45 min. @ 77°F (25°C) / 50% RH

Note: Cure times can be affected by a number of weather and jobsite conditions including but not limited to exposure to sunlight and wind, humidity, precipitation, and temperature.

Clean tools immediate after use with AlphaGuard PUMA Cleaner.

Not recommended for use over the following:

Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, corrugated or standing seam metal roof systems, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tar-based products.

- Not for use under continuous immersion.
- Do not thin.

ACCEPTABLE SURFACES/ SUBSTRATES

COVERAGE RATE

TEMPERATURE RECOMMENDATIONS

CURE TIMES

CLEAN UP

LIMITATIONS

AlphaGuard™ PUMA Primer - 107

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.