

Geogard[®] Primer

One-component, quick drying primer for urethane-based liquid applied products

DESCRIPTION

Geogard Primer is a single component primer designed to enhance adhesion to approved substrates and intercoat applications of urethane-based products.

BASIC USES

Geogard Primer is utilized to promote adhesion of newly applied urethane products to cured urethane products. It can also be used as primer over approved substrates.

GRADE

Brush, Roller, Spray

APPLICATION

Surface Preparation: Surface must be clean, dry, in sound condition, and free of dirt, debris, and contaminants. Existing wet roofing components must be identified and replaced. Deficient areas of existing system must be repaired. All repairs should be made with like materials matching the existing components and allowed to properly cure prior to application of liquid-applied products.

If the surface has a pre-existing coating, paint, or sealant, please contact Tremco for adhesion/compatibility testing and surface preparation recommendations.

Installation: Install product using one of the approved application methods evenly at the recommended coverage rate. Use wet mil gauges to monitor coverage rates throughout application.

Do not allow the product to puddle. Once the primer becomes dry and tacky (typically 30-45 mins) it can be top coated. Primer must be top coated prior to curing hard, glossy, and tack-free (typically within 12 hours). If this occurs, clean the primed area and re-prime following the application instructions listed above.

COVERAGE RATES

1/4 gal / 100 sq. ft. (0.1 L/m²) (4 wet mils)

Note: Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate.

TEMPERATURE RECOMMENDATIONS

Min Ambient: 40°F (4.4°C)

Max Ambient: 100°F (37.7°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.7°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product

CURE TIMES

Recoat Time: 15-30 minutes @ 77°F (25°C) / 50% RH

Note: Cure times can be effected by a number of weather and jobsite conditions including but not limited to exposure to sunlight and wind, humidity, precipitation, and temperature.

ACCEPTABLE ROOF SURFACES

BUR Gravel	BUR Smooth	Concrete	Metal	Metal Fluoropolymer	MB Granule	MB Smooth	Single-Ply	SPUF	Walls
	●				●	●	●		

Geogard® Primer

CLEAN UP

Clean equipment with xylene. Any spills or over-coating must be cleaned immediately before product dries.

LIMITATIONS

Not recommended for use over the following:

Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, corrugated or standing seam metal roof systems, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tar-based products.

- Not for use under continuous immersion

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Weight per Gallon (Liter)	10.32 lbs. (1.24 kg)	ASTM D 1475
Viscosity	20-50 CPS (mPas)	ASTM D 562
VOC	97 g/L	

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.
The information provided on this data page supersedes all previous data concerning this product and its application.
The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury to person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.