

AlphaGuard™ PUMA Cold Weather Mixing Charts

CANADA

ALPHAGUARD PUMA BASE COAT MIXING CHART

AlphaGuard PUMA Base Coat Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																																		
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0% Cold Weather Catalyst		6% FC Catalyst		1.05% Cold Weather Catalyst		5% FC Catalyst		1.4% Cold Weather Catalyst		5% FC Catalyst		2.1% Cold Weather Catalyst		5% FC Catalyst		3% Cold Weather Catalyst		5% FC Catalyst																
oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g						
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0	11	0.68	307	3 bags	1.89	0.12	54	9	0.56	256	2.5 bags	2.52	0.16	72	9	0.56	256	2.5 bags	3.79	0.24	107	9	0.56	256	2.5 bags	5.41	0.34	153	9	0.56	256	2.5 bags
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0	32	2.03	921	9.25 bags	5.69	0.36	161	27	1.69	768	7.75 bags	7.58	0.47	215	27	1.69	768	7.75 bags	11.37	0.71	322	27	1.69	768	7.75 bags	16.24	1.02	461	27	1.69	768	7.75 bags
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0	65	4.06	1842	18.5 bags	11.37	0.71	322	54	3.38	1535	15.5 bags	15.16	0.95	430	54	3.38	1535	15.5 bags	22.74	1.42	645	54	3.38	1535	15.5 bags	32.49	2.03	921	54	3.38	1535	15.5 bags

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA BASE COAT MIXING CHART

AlphaGuard PUMA Base Coat Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																													
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)													
	0% Cold Weather Catalyst		12% PUMA Catalyst		1.05% Cold Weather Catalyst		10% PUMA Catalyst		1.4% Cold Weather Catalyst		10% PUMA Catalyst		2.1% Cold Weather Catalyst		10% PUMA Catalyst		3% Cold Weather Catalyst		10% PUMA Catalyst											
oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g				
½ gal (5.64 lbs) 1.89 L (2.55 kg)	0.00	0.00	0.00	11	0.67	306	0.94	0.06	27	9	0.56	255	1.26	0.08	36	9	0.56	255	1.89	0.12	54	9	0.56	255	2.70	0.17	77	9	0.56	255
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0.00	22	1.35	613	1.89	0.12	54	18	1.13	511	2.52	0.16	72	18	1.13	511	3.79	0.24	107	18	1.13	511	5.41	0.34	153	18	1.13	511
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0.00	65	4.06	1842	5.69	0.36	161	54	3.38	1535	7.58	0.47	215	54	3.38	1535	11.37	0.71	322	54	3.38	1535	16.24	1.02	461	54	3.38	1535
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0.00	130	8.12	3684	11.37	0.71	322	108	6.77	3070	15.16	0.95	430	108	6.77	3070	22.74	1.42	645	108	6.77	3070	32.49	2.03	921	108	6.77	3070

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA TOP COAT MIXING CHART

AlphaGuard PUMA Top Coat Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																																		
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0% Cold Weather Catalyst		6% FC Catalyst		1.05% Cold Weather Catalyst		5% FC Catalyst		1.4% Cold Weather Catalyst		5% FC Catalyst		2.1% Cold Weather Catalyst		5% FC Catalyst		3% Cold Weather Catalyst		5% FC Catalyst																
oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g						
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0	9	0.55	248	2.5 bags	7	0.46	207	2.04	0.13	58	1/2 bags	2.04	0.13	58	7	0.46	207	2 bags	3.06	0.19	87	7	0.46	207	2 bags	4.37	0.27	87	7	0.46	207	2 bags
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0	26	1.64	745	7.5 bags	4.60	0.29	130	22	1.37	621	6.25 bags	6.13	0.38	174	22	1.37	621	6.25 bags	9.19	0.57	261	22	1.37	621	6.25 bags	13.13	0.82	372	22	1.37	621	6.25 bags
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0	53	3.28	1489	15 bags	9.19	0.57	261	44	2.74	1241	12.5 bags	12.26	0.77	347	44	2.74	1241	12.5 bags	18.39	1.15	521	44	2.74	1241	12.5 bags	26.26	1.64	745	44	2.74	1241	12.5 bags

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA TOP COAT MIXING CHART

AlphaGuard PUMA Top Coat Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																													
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)													
	0% Cold Weather Catalyst		12% PUMA Catalyst		1.05% Cold Weather Catalyst		10% PUMA Catalyst		1.4% Cold Weather Catalyst		10% PUMA Catalyst		2.1% Cold Weather Catalyst		10% PUMA Catalyst		3% Cold Weather Catalyst		10% PUMA Catalyst											
oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g				
½ gal (4.56 lbs) 1.89 L (2.06 kg)	0.00	0.00	0.00	10	0.54	247	0.76	0.05	22	7	0.45	206	1.02	0.06	29	7	0.45	206	1.53	0.10	43	7	0.45	206	2.18	0.14	62	7	0.45	206
1 gal (9.12 lbs) 3.78 L (4.13 kg)	0.00	0.00	0.00	20	1.09	496	1.53	0.10	43	15	0.91	413	2.04	0.13	58	15	0.91	413	3.06	0.19	87	15	0.91	413	4.37	0.27	124	15	0.91	413
3 gal (27.36 lbs) 11.34 L (12.41 kg)	0.00	0.00	0.00	60	3.28	1489	4.60	0.29	130	44	2.74	1241	6.13	0.38	174	44	2.74	1241	9.19	0.57	261	44	2.74	1241	13.13	0.82	372	44	2.74	1241
6 gal (54.72 lbs) 22.68 L (24.82 kg)	0.00	0.00	0.00	105	6.57	2978	9.19	0.57	261	88	5.47	2482	12.26	0.77	347	88	5.47	2482	18.39	1.15	521	88	5.47	2482	26.26	1.64	745	88	5.47	2482

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

AlphaGuard™ PUMA Cold Weather Mixing Charts

ALPHAGUARD PUMA CLEAR COAT MIXING CHART

AlphaGuard PUMA Clear Coat Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																											
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)											
	0% Cold Weather Catalyst		6% FC Catalyst		Cold Weather Catalyst		FC Catalyst		Cold Weather Catalyst		FC Catalyst		Cold Weather Catalyst		FC Catalyst		Cold Weather Catalyst		FC Catalyst									
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0	8	0.49	222	2.25 bags																					
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0	24	1.47	667	6.75 bags																					
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0	47	2.94	1334	13.5 bags																					

Contact Tremco Product Group for Information

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA CLEAR COAT MIXING CHART

AlphaGuard PUMA Clear Coat Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																											
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)											
	0% Cold Weather Catalyst		12% PUMA Catalyst		Cold Weather Catalyst		PUMA Catalyst		Cold Weather Catalyst		PUMA Catalyst		Cold Weather Catalyst		PUMA Catalyst		Cold Weather Catalyst		12% PUMA Catalyst									
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	
½ gal (4.08 lbs) 1.89 L (1.85 kg)	0.00	0.00	0.00	9	0.49	222																						
1 gal (8.17 lbs) 3.78 L (3.70 kg)	0.00	0.00	0.00	18	0.98	444																						
3 gal (24.51 lbs) 11.34 L (11.11 kg)	0.00	0.00	0.00	47	2.94	1333																						
6 gal (49.02 lbs) 22.68 L (22.23 kg)	0.00	0.00	0.00	94	5.88	2668																						

Contact Tremco Product Group for information.

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA PRIMER-107 MIXING CHART

AlphaGuard PUMA Primer-107 Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																																		
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0.7% Cold Weather Catalyst		6% FC Catalyst		1.4% Cold Weather Catalyst		6% FC Catalyst		2.1% Cold Weather Catalyst		6% FC Catalyst		2.8% Cold Weather Catalyst		6% FC Catalyst		4.2% Cold Weather Catalyst		6% FC Catalyst																
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags								
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.92	0.06	26	8	0.49	224	2.25 bags	1.85	0.12	52	8	0.49	224	2.25 bags	2.77	0.17	79	8	0.49	224	2.25 bags	3.69	0.23	105	8	0.49	224	2.25 bags	5.54	0.35	157	8	0.49	224	2.25 bags
3 gal (33.84 lbs) 11.34 L (15.35 kg)	2.78	0.17	79	24	1.49	674	6.75 bags	5.55	0.35	157	24	1.49	674	6.75 bags	8.33	0.52	236	24	1.49	674	6.75 bags	11.10	0.69	315	24	1.49	674	6.75 bags	16.65	1.04	472	24	1.49	674	6.75 bags
6 gal (67.68 lbs) 22.68 L (30.70 kg)	5.55	0.35	157	48	2.97	1349	13.5 bags	11.10	0.69	315	48	2.97	1349	13.5 bags	16.65	1.04	472	48	2.97	1349	13.5 bags	22.20	1.39	629	48	2.97	1349	13.5 bags	33.30	2.08	944	48	2.97	1349	13.5 bags

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA PRIMER-107 MIXING CHART

AlphaGuard PUMA Primer-107 Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																														
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)														
	0.7% Cold Weather Catalyst		12% PUMA Catalyst		1.4% Cold Weather Catalyst		12% PUMA Catalyst		2.1% Cold Weather Catalyst		12% PUMA Catalyst		2.8% Cold Weather Catalyst		12% PUMA Catalyst		4.2% Cold Weather Catalyst		12% PUMA Catalyst												
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags				
½ gal (4.13 lbs) 1.89 L (1.87 kg)	0.46	0.03	13	9	0.49	224		0.92	0.06	26	8	0.49	224	1.39	0.09	39	8	0.49	224	1.85	0.12	52	8	0.49	224	2.77	0.17	79	8	0.49	224
1 gal (8.26 lbs) 3.78 L (3.74 kg)	0.92	0.06	26	18	0.99	449		1.85	0.12	52	16	0.99	449	2.77	0.17	79	16	0.99	449	3.69	0.23	105	16	0.99	449	5.54	0.35	157	16	0.99	449
3 gal (24.78 lbs) 11.34 L (11.24 kg)	2.78	0.17	79	54	2.97	1349		5.55	0.35	157	48	2.97	1349	8.33	0.52	236	48	2.97	1349	11.10	0.69	315	48	2.97	1349	16.65	1.04	472	48	2.97	1349
6 gal (49.56 lbs) 22.68 L (22.48 kg)	5.55	0.35	157	95	5.95	2698		11.10	0.69	315	95	5.95	2698	16.65	1.04	472	95	5.95	2698	22.20	1.39	629	95	5.95	2698	33.30	2.08	944	95	5.95	2698

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

AlphaGuard™ PUMA Cold Weather Mixing Charts

ALPHAGUARD PUMA THIX MIXING CHART

AlphaGuard PUMA THIX Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																																		
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0% Cold Weather Catalyst		6% FC Catalyst		1.05% Cold Weather Catalyst		5% FC Catalyst		1.4% Cold Weather Catalyst		5% FC Catalyst		2.1% Cold Weather Catalyst		5% FC Catalyst		3% Cold Weather Catalyst		5% FC Catalyst																
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags												
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0	11	0.68	307	3 bags	1.89	0.12	54	9	0.56	256	2.5 bags	2.52	0.16	72	9	0.56	256	2.5 bags	3.79	0.24	107	9	0.56	256	2.5 bags	5.41	0.34	153	9	0.56	256	2.5 bags
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0	32	2.03	921	9.25 bags	5.69	0.36	161	27	1.69	768	7.75 bags	7.58	0.47	215	27	1.69	768	7.75 bags	11.37	0.71	322	27	1.69	768	7.75 bags	16.24	1.02	461	27	1.69	768	7.75 bags
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0	65	4.06	1842	18.5 bags	11.37	0.71	322	54	3.38	1535	15.5 bags	15.16	0.95	430	54	3.38	1535	15.5 bags	22.74	1.42	645	54	3.38	1535	15.5 bags	32.49	2.03	921	54	3.38	1535	15.5 bags

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA THIX MIXING CHART

AlphaGuard PUMA THIX Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																													
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)													
	0% Cold Weather Catalyst		12% PUMA Catalyst		1.05% Cold Weather Catalyst		10% PUMA Catalyst		1.4% Cold Weather Catalyst		10% PUMA Catalyst		2.1% Cold Weather Catalyst		10% PUMA Catalyst		3% Cold Weather Catalyst		10% PUMA Catalyst											
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g						
½ gal (5.64 lbs) 1.89 L (2.55 kg)	0.00	0.00	0.00	12	0.67	306	0.94	0.06	27	9	0.56	255	1.26	0.08	36	9	0.56	255	1.89	0.12	54	9	0.56	255	2.70	0.17	77	9	0.56	255
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0.00	25	1.35	613	1.89	0.12	54	18	1.13	511	2.52	0.16	72	18	1.13	511	3.79	0.24	107	18	1.13	511	5.41	0.34	153	18	1.13	511
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0.00	74	4.06	1842	5.69	0.36	161	54	3.38	1535	7.58	0.47	215	54	3.38	1535	11.37	0.71	322	54	3.38	1535	16.24	1.02	461	54	3.38	1535
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0.00	130	8.12	3684	11.37	0.71	322	108	6.77	3070	15.16	0.95	430	108	6.77	3070	22.74	1.42	645	108	6.77	3070	32.49	2.03	921	108	6.77	3070

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA QUICK FLASH MIXING CHART

AlphaGuard PUMA Quick Flash Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																																		
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0% Cold Weather Catalyst		6% FC Catalyst		1.05% Cold Weather Catalyst		5% FC Catalyst		1.4% Cold Weather Catalyst		5% FC Catalyst		2.1% Cold Weather Catalyst		5% FC Catalyst		3% Cold Weather Catalyst		5% FC Catalyst																
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags								
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0	11	0.69	311	3.25 bags	1.92	0.12	54	9	0.57	259	2.75 bags	2.56	0.16	73	9	0.57	259	2.75 bags	3.84	0.24	109	9	0.57	259	2.75 bags	5.48	0.34	155	9	0.57	259	2.75 bags
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0	33	2.06	933	9.5 bags	5.76	0.36	163	27	1.71	778	7.75 bags	7.68	0.48	218	27	1.71	778	7.75 bags	11.52	0.72	327	27	1.71	778	7.75 bags	16.46	1.03	467	27	1.71	778	7.75 bags
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0	66	4.11	1866	18.75 bags	11.52	0.72	327	55	3.43	1555	15.5 bags	15.36	0.96	435	55	3.43	1555	15.5 bags	23.04	1.44	653	55	3.43	1555	15.5 bags	32.91	2.06	933	55	3.43	1555	15.5 bags

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA QUICK FLASH MIXING CHART

AlphaGuard PUMA Quick Flash Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																													
	32°F (0°C)				14°F (-10°C)				5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)													
	0% Cold Weather Catalyst		12% PUMA Catalyst		1.05% Cold Weather Catalyst		10% PUMA Catalyst		1.4% Cold Weather Catalyst		10% PUMA Catalyst		2.1% Cold Weather Catalyst		10% PUMA Catalyst		3% Cold Weather Catalyst		10% PUMA Catalyst											
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g						
½ gal (5.71 lbs) 1.89 L (2.59 kg)	0.00	0.00	0.00	12	0.69	311	0.96	0.06	27	9	0.57	259	1.28	0.08	36	9	0.57	259	1.92	0.12	54	9	0.57	259	2.74	0.17	78	9	0.57	259
1 gal (11.43 lbs) 3.78 L (5.18 kg)	0.00	0.00	0.00	25	1.37	622	1.92	0.12	54	18	1.14	518	2.56	0.16	73	18	1.14	518	3.84	0.24	109	18	1.14	518	5.48	0.34	155	18	1.14	518
3 gal (34.29 lbs) 11.34 L (15.55 kg)	0.00	0.00	0.00	75	4.11	1866	5.76	0.36	163	55	3.43	1555	7.68	0.48	218	55	3.43	1555	11.52	0.72	327	55	3.43	1555	16.46	1.03	467	55	3.43	1555
6 gal (68.58 lbs) 22.68 L (31.10 kg)	0.00	0.00	0.00	132	8.23	3732	11.52	0.72	327	110	6.86	3110	15.36	0.96	435	110	6.86	3110	23.04	1.44	653	110	6.86	3110	32.91	2.06	933	110	6.86	3110

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

AlphaGuard™ PUMA Cold Weather Mixing Charts

ALPHAGUARD PUMA SR MIXING CHART

AlphaGuard PUMA SR Amount	AlphaGuard PUMA Cold Weather Catalyst & FC Catalyst Powder Amounts by Temperature Ranges																																						
	32°F (0°C)						14°F (-10°C)						5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0% Cold Weather Catalyst		6% FC Catalyst		1.05% Cold Weather Catalyst		5% FC Catalyst		1.4% Cold Weather Catalyst		5% FC Catalyst		2.1% Cold Weather Catalyst		5% FC Catalyst		3% Cold Weather Catalyst		5% FC Catalyst																				
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags																
1 gal (11.28 lbs) 3.78 L (5.11 kg)	0.00	0.00	0	8	0.47	213	2.25 bags	1.31	0.08	37		6	0.39	178	1.75 bags	1.75	0.11	50		6	0.39	178	1.75 bags	2.63	0.16	75		6	0.39	178	1.75 bags	3.76	0.23	107		6	0.39	178	1.75 bags
3 gal (33.84 lbs) 11.34 L (15.35 kg)	0.00	0.00	0	23	1.41	640	6.5 bags	3.95	0.25	112		19	1.18	533	5.5 bags	5.26	0.33	149		19	1.18	533	5.5 bags	7.90	0.49	224		19	1.18	533	5.5 bags	11.28	0.71	320		19	1.18	533	5.5 bags
6 gal (67.68 lbs) 22.68 L (30.70 kg)	0.00	0.00	0	45	2.82	1280	13 bags	7.90	0.49	224		38	2.35	1067	10.75 bags	10.53	0.66	299		38	2.35	1067	10.75 bags	15.80	0.99	448		38	2.35	1067	10.75 bags	22.57	1.41	640		38	2.35	1067	10.75 bags

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

ALPHAGUARD PUMA SR MIXING CHART

AlphaGuard PUMA SR Amount	AlphaGuard PUMA Cold Weather Catalyst & PUMA Powder Catalyst Amounts by Temperature Ranges																																						
	32°F (0°C)						14°F (-10°C)						5°F (-15°C)				-4°F (-20°C)				-22°F (-30°C)																		
	0% Cold Weather Catalyst		12% PUMA Catalyst		1.05% Cold Weather Catalyst		10% PUMA Catalyst		1.4% Cold Weather Catalyst		10% PUMA Catalyst		2.1% Cold Weather Catalyst		10% PUMA Catalyst		3% Cold Weather Catalyst		10% PUMA Catalyst																				
	oz	lbs	g	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags	oz	lbs	g	100g bags																
½ gal (3.92 lbs) 1.89 L (1.77 kg)	0.00	0.00	0.00	8	0.47	212	0.66	0.04	19	6	0.39	177	0.87	0.05	25	6	0.39	177	1.31	0.08	37	6	0.39	177	1.87	0.12	53	6	0.39	177									
1 gal (7.84 lbs) 3.78 L (3.55 kg)	0.00	0.00	0.00	17	0.94	426	1.31	0.08	37	13	0.78	355	1.75	0.11	50	13	0.78	355	2.63	0.16	75	13	0.78	355	3.76	0.23	107	13	0.78	355									
3 gal (23.52 lbs) 11.34 L (10.66 kg)	0.00	0.00	0.00	51	2.82	1279	3.95	0.25	112	38	2.35	1066	5.26	0.33	149	38	2.35	1066	7.90	0.49	224	38	2.35	1066	11.28	0.71	320	38	2.35	1066									
6 gal (47.04 lbs) 22.68 L (21.33 kg)	0.00	0.00	0.00	90	5.64	2560	7.90	0.49	224	75	4.70	2133	10.53	0.66	299	75	4.70	2133	15.80	0.99	448	75	4.70	2133	22.57	1.41	640	75	4.70	2133									

*** YOU MUST MIX COLD WEATHER CATALYST INTO THE RESIN PRIOR TO ADDING THE POWDER PUMA CATALYST!**
* Follow precise catalyst quantities for cold weather applications.

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building Maintenance is a part of the Tremco Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.