

AlphaGuard™ PUMA Standard Mixing Charts

Canada

AG PUMA BASE COAT AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE														
	70-95°F (21-35°C)			60-70°F (15-21°C)			40-60°F (5-15°C)			32-40°F (0-5°C)			< 32°F (< 0°C)		
	2% Catalyst			4% Catalyst			8% Catalyst			12% Catalyst					
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (5.64 lbs) 1.89 L (2.55 kg)	2	0.11	51	4	0.22	102	7	0.45	204	11	0.67	306			
1 gal (11.28 lbs) 3.78 L (5.11 kg)	4	0.23	102	7	0.45	204	14	0.90	409	22	1.35	613			
3 gal (33.84 lbs) 11.34 L (15.35 kg)	11	0.68	307	22	1.35	614	43	2.71	1228	65	4.06	1842			
6 gal (67.68 lbs) 22.68 L (300 kg)	22	1.35	614	43	2.71	1228	87	5.41	2456	130	8.12	3684			

* AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

AG PUMA TOP COAT AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C)			60-70°F (15-21°C)			40-60°F (5-15°C)			32-40°F (0-5°C)			< 32°F (< 0°C)		
	2% Catalyst			4% Catalyst			8% Catalyst			12% Catalyst					
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (4.56 lbs) 1.89 L (2.06 kg)	2	0.09	41	3	0.18	82	7	0.36	165	10	0.54	247			
1 gal (9.12 lbs) 3.78 L (4.13 kg)	3	0.18	83	7	0.36	165	13	0.73	330	20	1.09	496			
3 gal (27.36 lbs) 11.34 L (12.41 kg)	10	0.55	248	20	1.09	496	40	2.19	993	60	3.28	1489			
6 gal (54.72 lbs) 22.68 L (24.82 kg)	18	1.09	496	35	2.19	993	70	4.38	1986	105	6.57	2978			

* AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

AG PUMA CLEAR COAT AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C)			60-70°F (15-21°C)			40-60°F (5-15°C)			32-40°F (0-5°C)			< 32°F (< 0°C)		
	2% Catalyst			4% Catalyst			8% Catalyst			12% Catalyst					
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (4.08 lbs) 1.89 L (1.85 kg)	1	0.08	37	3	0.16	74	6	0.33	148	9	0.49	222			
1 gal (8.17 lbs) 3.78 L (3.70 kg)	3	0.16	74	6	0.33	148	12	0.65	296	18	0.98	444			
3 gal (24.51 lbs) 11.34 L (11.11 kg)	9	0.49	222	18	0.98	444	36	1.96	889	53	2.94	1333			
6 gal (49.02 lbs) 22.68 L (22.23 kg)	16	0.98	445	31	1.96	889	63	3.92	1778	94	5.88	2668			

* AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

AG PUMA PRIMER - 107 AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C)			60-70°F (15-21°C)			40-60°F (5-15°C)			32-40°F (0-5°C)			< 32°F (< 0°C)		
	2% Catalyst			4% Catalyst			8% Catalyst			12% Catalyst					
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (4.13 lbs) 1.89 L (1.87 kg)	1	0.08	37	3	0.16	75	6	0.33	150	9	0.49	224			
1 gal (8.26 lbs) 3.78 L (3.74 kg)	3	0.16	75	6	0.33	150	12	0.66	299	18	0.99	449			
3 gal (24.78 lbs) 11.34 L (11.24 kg)	9	0.50	225	18	0.99	450	36	1.98	899	54	2.97	1349			
6 gal (49.56 lbs) 22.68 L (22.48 kg)	16	0.99	450	32	1.98	899	63	3.96	1798	95	5.95	2698			

* AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

Contact Tremco
Product Group
for information.

Contact Tremco
Product Group
for information.

Contact Tremco
Product Group
for information.

Contact Tremco
Product Group
for information.

AlphaGuard™ PUMA Standard Mixing Charts

AG PUMA THIX AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C) 2% Catalyst			60-70°F (15-21°C) 4% Catalyst			40-60°F (5-15°C) 8% Catalyst			32-40°F (0-5°C) 12% Catalyst			< 32°F (< 0°C)		
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (5.64 lbs) 1.89 L (2.55 kg)	2	0.11	51	4	0.22	102	8	0.45	204	12	0.67	306	Contact Tremco Product Group for information.		
1 gal (11.28 lbs) 3.78 L (5.11 kg)	4	0.23	102	8	0.45	204	16	0.90	409	25	1.35	613			
3 gal (33.84 lbs) 11.34 L (15.35 kg)	12	0.68	307	25	1.35	614	49	2.71	1228	74	4.06	1842			
6 gal (67.68 lbs) 22.68 L (30.70 kg)	22	1.35	614	43	2.71	1228	87	5.41	2456	130	8.12	3684			

*AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

AG PUMA QUICK FLASH AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C) 2% Catalyst			60-70°F (15-21°C) 4% Catalyst			40-60°F (5-15°C) 8% Catalyst			32-40°F (0-5°C) 12% Catalyst			< 32°F (< 0°C)		
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (5.71 lbs) 1.89 L (2.59 kg)	2	0.11	52	4	0.23	104	8	0.46	207	12	0.69	311	Contact Tremco Product Group for information.		
1 gal (11.43 lbs) 3.78 L (5.18 kg)	4	0.23	104	8	0.46	207	17	0.91	414	25	1.37	622			
3 gal (34.29 lbs) 11.34 L (15.55 kg)	12	0.69	311	25	1.37	622	50	2.74	1244	75	4.11	1866			
6 gal (68.58 lbs) 22.68 L (31.10 kg)	22	1.37	622	44	2.74	1244	88	5.49	2488	132	8.23	3732			

*AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

AG PUMA SR AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C) 2% Catalyst			60-70°F (15-21°C) 4% Catalyst			40-60°F (5-15°C) 8% Catalyst			32-40°F (0-5°C) 12% Catalyst			< 32°F (< 0°C)		
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (3.92 lbs) 1.89 L (1.77 kg)	1	0.08	35	3	0.16	71	6	0.31	142	8	0.47	212	Contact Tremco Product Group for information.		
1 gal (7.84 lbs) 3.78 L (3.55 kg)	3	0.16	71	6	0.31	142	11	0.63	284	17	0.94	426			
3 gal (23.52 lbs) 11.34 L (10.66 kg)	9	0.47	213	17	0.94	426	34	1.88	853	51	2.82	1279			
6 gal (47.04 lbs) 22.68 L (21.33 kg)	15	0.94	427	30	1.88	853	60	3.76	1706	90	5.64	2560			

*AlphaGuard PUMA Catalyst amounts listed on this chart are minimum required quantities.

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury to person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.