


TremPly® KEE and KEE FB Single Ply Systems

A reinforced polyester knit fabric with a proprietary hybrid thermoplastic alloy coating



FEATURES

- Elvaloy KEE flexibilizer
- Heavy duty reinforcement
- Full bond around fiber reinforcement
- Fleeceback and smooth versions

BENEFITS

- Superior flexibility, UV resistance and chemical resistance
- Excellent tear strength and puncture resistance
- Maximum seam strength for long term performance
- Multiple application methods to meet project specific needs

DESCRIPTION

TremPly® KEE and KEE FB (Fleeceback) Systems not only meet or exceed the minimum physical property requirements enumerated in ASTM D6754 Standard Specification for Ketone Ethylene Ester (KEE) based sheet roofing, but exceed the physical properties and performance characteristics of much thicker competitive products. TremPly KEE membranes are available in nominal 45 and 60 mil thickness; smooth and fleeceback versions; and in white, gray and tan which can all help an organization meet LEED requirements. All TremPly KEE Roofing Membranes are constructed using high tenacity/heavy weight yarns to create a base fabric reinforcement to impart superior puncture, tensile and tear resistance properties. The base polyester fabrics are primed with a unique and proprietary adhesive coat that lays the foundation to physically bond the KEE coatings to the “fiber” to maximize seam strength and overall membrane performance. TremPly KEE is coated to provide superior hot air welding characteristics, extreme UV resistance, broad chemical resistance and long-term flexibility and reparability for the installed roofing membrane system. TremPly KEE Roofing Systems have excellent tear, puncture, fungus, algae and flame resistance, making them among the most sustainable roofing systems available.

BASIC USES

TremPly KEE and KEE FB single ply roofing systems are designed to provide superior performance and exceptional value; the white, tan or gray surfaces absorb much less heat than a black roof, which can help lower a facility’s energy use and improve its appearance. They are excellent choices for roof overlays, replacement and new construction alike.

APPLICATION

TremPly KEE Roofing Systems carry extensive FM Global and Underwriters Laboratories’ approvals. TremPly KEE Roofing Systems can be installed by mechanically fastening or adhering the membrane bonding adhesive. TremPly KEE can also be installed in typical ballast configurations using conventional stone or paver ballast. Field seaming is accomplished by fusing the thermoplastic membrane with conventional hot air welding equipment.

APPROVED ATTACHMENT METHODS

TremPly KEE is manufactured in 37” and 74” wide by 100’ long rolls. KEE FB is manufactured in 72” wide by 80’ long rolls.

	TREMPLY KEE	TREMPLY KEE FB
POWERply Endure BIO Adhesive	No	Yes
Tremply KEE FB Bonding Adhesive	No	Yes
Tremply KEE LV Bonding Adhesive	Yes	No
Tremply KEE WBII Bonding Adhesive	No	Yes
Hot Asphalt	No	Yes
TremPLY KEE Plus Stress Plates	Yes	Yes

The application information provided in this data sheet serves as general guidance. Please refer to Tremco application guides and project specific specifications or consult with your local Tremco Roofing sales representative for project specific application requirements. Refer to the Safety Data Sheet (SDS) for material precautions.

TremPly® KEE and KEE FB Single Ply Systemstems

PHYSICAL PROPERTIES

PROPERTY	ASTM D6754	TREPLY KEE ANDKEE FB
Thickness <i>ASTM D 751 (inches)</i>	.032	.045/.060
Thickness over Fiber <i>Optical method (inches)</i>	.007	.014/.016
Breaking Strength (MD/XMD) <i>D 751 proc. B. - strip (lbf/in)</i>	337	520/406
Elongation at Break (MD/XMD) <i>D 751 - strip</i>	18	22/20
Tear Strength (MD/XMD) <i>ASTM D 751 proc. B. Tongue Tear (lbf)</i>	76	125/145
Linear Dimensional Change (MD/XMD) <i>ASTM D 1204 max (%)</i>	1.3	-0.6/-1
Fabric Adhesion <i>D 751 min. (lb/in)</i>	19	no peel
Low Temperature Bend <i>ASTM D 2136 (0f)</i>	-30	-30
Retention of Properties After Heat Aging		
<i>Practice D 3045 - 1760f /56 days</i>		
Breaking Strength min. <i>ASTM D 751 proc. B. (lbf/in.)</i>	90	90
Elongation at break <i>ASTM D 751 proc. B.</i>	19/18	20/20
Low Temperature Bend <i>ASTM D 2136 (°F) ASTM D 751</i>	-30	pass
Change in Weight after Exposure in Water <i>D 471 1580f one side only, max. (%)</i>	+6.0	0.7
Seam Strength <i>D 751 Grab Method, min. (lbf)</i>	440	800
Hydrostatic Resistance (psi) <i>ASTM D751</i>	590	>1,000
Static Puncture Resistance <i>ASTM D 5602 (99 lbf)</i>	pass	pass
Dynamic Impact / Puncture Resistance <i>ASTM D 5635 min. (J)</i>	10	pass
Accelerated Weathering <i>Practice G 155 / 5,000 h xenon</i>		
Cracking (7x magnification)	none	none
Crazing (7x magnification)	none	none
Accelerated Weathering <i>Practice G 154 / 5,000 h UVA</i>		
Cracking (7x magnification)	none	none
Crazing (7x magnification)	none	none
Fungi Resistance <i>Practice G 21, 28 days Sustained Growth</i>	no growth	none
Abrasion <i>D 3389 H-18 wheel 1,000 g load, (min. cycles)</i>	1,500	>2,000

ENERGY ATTRIBUTES

PROPERTY	WHITE	GRAY	TAN
Solar Reflectance-DC6 White Initial <i>ASTM C1549</i>	0.87	0.69	0.72
Solar Reflectance (3 yr. Aged) <i>ASTM C1549</i>	0.71	0.61	0.63
Initial Thermal Emittance <i>ASTM C1371</i>	0.85	0.89	0.88
Thermal Emittance 3 yr Aged <i>ASTM C1371</i>	0.84	0.89	0.89
Solar Reflective Index (SRI) <i>ASTM E1980</i>	110	84	88
Solar Reflective Index (SRI) 3 yr aged <i>ASTM E1980</i>	86	73	76
LEED 2.2 Heat Island Effect (SRI> 78) <i>SS Credit 7.2</i>	1 credit	1 credit	1 credit

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.

TremPly® KEE and KEE FB Single Ply Systems



Roofing & Building Maintenance

www.tremcoroofing.com

3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.