# TremPly® Max TPO FB Single Ply Roofing Systems

Environmentally Friendly, Long-Lasting Single Ply Adhered Roofing System

#### **FEATURES**

### **BENEFITS**

Great Value

• Excellent performance at a cost-effective price.

Excellent Seam Strength

• Heat-welded seams provide greater seam strength to taped and other seams.

Long-term Weathering • Excellent long-term heat and UV resistance.

**Energy Saving** 

• Highly reflective and emissive white surface can help reduce energy use and urban heat island effect.

Inherently Flexible

• No need for plasticizers.

**Fungal Resistant** 

• Doesn't require biocides.



# **DESCRIPTION**

TremPly\* Max TPO FB Single Ply Roofing System is a fleece back thermoplastic roofing membrane. It is offered in 5-foot and 10-foot-wide sheets that feature heat welded seam integrity and overall exceptional value. The TremPly MAX TPO FB material has been formulated for maximum weatherability and exceeds the ASTM heat aging requirement by 4 times.

**BASIC USES** 

TremPly Max TPO FB is offered white, gray and tan colors with 50 mil, 60 mil, 70 mil and 80 mil thickness. TremPly Max TPO FB is also available in a smooth back version which is detailed on a separate data sheet. They are excellent choices for roof overlays, replacement and new construction alike. Tremco also offers TremPly TPO as a more economical alternative to the TremPly Max TPO.

COLOR

White

GRADE

TremPly Max TPO FB is offered in 50mil, 60mil, 70mil and 80mil thicknesses. Original TremPly TPO and Fleeceback versions are available and detailed on separate data sheets.

STORAGE LIFE

Store rolls on their sides on pallets or shelving in a dry area. Jobsite specific be sure to cover or tarp when not in use.

**COVERAGE RATE** 

**APPLICATIONS** 

Available in 10'x100' (1,000 sq. ft.) and 5'x100' sheets (500 sq. ft.)

TremPly Max TPO FB is available as a fully adhered roofing system. Field seaming is accomplished by fusing the thermoplastic membrane with conventional hot air welding equipment. It comes with a full line of readily available, pre-fabricated accessories designed to save time and money. TremPly Max TPO FB Roofing Systems carry extensive FM Global and Underwriters Laboratories' approvals.

Please refer to Tremco application guides and project specific specifications or consult with your local Tremco Roofing sales representative for project specific application requirements.

**LIMITATIONS** 

Follow recommendations for applicable adhesives or installation methods in low temperature situations.

# **TremPly® Max TPO FB Single Ply Roofing Systems**

## PHYSICAL PROPERTIES

PROPERTY	ASTM D6878 MINIMUM	TPO 50 MIL	TPO 60 MIL	TPO 70 MIL	TPO 80 MIL
Normal Thickness ASTM D751	0.039" (min.) (0.99 mm)	0.050" (1.27 mm)	0.060" (1.52 mm)	0.070" (1.78 mm)	0.080" (2.03 mm)
Breaking Strength ASTM D751	220 lbf/in. (38.5 kn/m)	375 lbf x 330 lbf	400 lbf x 360 lbf	400 lbf x 360 lbf	440 lbf x 390 lbf
Grab Method		(559 x 492 kg/m)	(596 x 536 kg/m)	(596 x 536 kg/m)	(656 x 581 kg/m)
Factory Seam Strength ASTM D751	66 lbf (98.34 kg/m)	140 lbf (209 kg/m)	140 lbf (209 kg/m)	140 lbf (209 kg/m)	140 lbf (209 kg/m)
		(membrane failure)	(membrane failure)	(membrane failure)	(membrane failure)
Elongation at break ASTM D751	15%	30%	30%	30%	30%
Heat Aging ASTM D751	90% retention of Breaking	100%	100%	100%	100%
	Strength & Elongation at break				
Tear Strength ASTM D751 8" x 8"	55 lbf (81.95 kg/m)	70 lbf x 130 lbf	70 lbf x 130 lbf	70 lbf x 130 lbf	100 lbf x 180 lbf
(203 x 203 mm) Sample		(104 x 194 kg/m)	(104 x 194 kg/m)	(104 x 194 kg/m)	(149 x 268 kg/m)
Puncture Resistance FTM 101C	Not Established	380 (172 kg)	380 (172 kg)	380 (172 kg)	380 (172 kg)
Method 2031					
Cold Brittleness ASTM D2137	(-40°C)	-40° C	-40° C	-40° C	-40° C
Permeance ASTM E96	Not Established	0.08 Perms	0.08 Perms	0.08 Perms	0.08 Perms
Dimensional Change ASTM D1204	(+/-1%)	0.40%	0.40%	0.40%	0.40%
@ 158°F (70°C), 6 hrs.					
Water Absorption ASTM D471	(+/-3.0%)	0.70%	0.70%	0.70%	0.70%
@ 158°F (70°C), 1 week					
Hydrostatic Resistance ASTM D751	Not Established	430 psi	430 psi	430 psi	430 psi
Method D					
Ozone Resistance ASTM 1149	No visible deterioration	No visible deterioration	No visible deterioration	No visible deterioration	No visible deterioration
	@ 7x magnification	@ 7x magnification	@ 7x magnification	@ 7x magnification	@ 7x magnification
Reflectivity (white) initial/aged	N/A	0.84/0.72	0.84/0.72	0.84/0.72	0.84/0.72
ASTM C1549, ASTM E903					
Emissivity (white) Initial/aged	N/A	0.84/0.91	0.84/0.91	0.84/0.91	0.84/0.91
ASTM C1371, ASTM E403					
Weather Resistance ASTM G155	10,080 KJ/(m <sup>2</sup> x nm)	>46,000 KJ/(m <sup>2</sup> . nm)			
/D6878	at 340 nm	at 340 nm	at 340 nm	at 340 nm	at 340 nm
Heat Aging ASTM D573	240°F (115°C) for 32 weeks	128 weeks	128 weeks	128 weeks	128 weeks
Thickness Above Scrim ASTM D7635	Min 30% of Total Thickness	17.9 mil (Nominal)	21.5 mil (Nominal)	25.7 mil (Nominal)	31.5 mil (Nominal)

**MAINTENANCE** 

**TECHNICAL SUPPORT** 



Roofing & Building Maintenance

ww.tremcoroofing.com 3735 Green Road Beachwood, Ohio 44122 1.800.852.6013

50 Beth Nealson Drive Toronto, Ontario M4H 1M6 1.800.668.9879 Tremco Roofing & Building Maintenance is a part of the Tremco Construction Products Group Note: This data based on typical product performance for 45-mil membrane, and are subject to normal manufacturing tolerances and variances. Certain data are provided in MD (machine direction) x CMD (cross machine direction) format. Visit www.tremcoroofing.com for latest data. Important Note: Tremco TPO membranes meet and/or exceed ASTM D-6870 standards for thermoplastic TPO membranes.

Your local Tremco Roofing representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the service of the Tremco Service Staff.

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and sesume the risk of a year failure injury of presents and loss or liability resulting from the handling storage or use of the conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.